



## MATERIAL SELECTION GUIDE

### PVC

#### AUTOMOTIVE WIRE JACKET COMPOUNDS

Product	Durometer 10 Sec.	S.G.	Temp °C	Tensile	Elongation	LOI	Application
OW134	64 "D"	1.34	105	3000	250	30	SEMI-RIGID 105°, JACKET
OW135	93	1.35	105	2800	360	29	THHN, THWN, MTW, 60 OIL, JACKET
OW834	85	1.34	80	2500	300	25	GP JACKET
OW837 GPT	92	1.35	80	2700	200	30	GPT JACKET