



MATERIAL SELECTION GUIDE

POLYMER ALLOY

FLEXIBLE CORD JACKET COMPOUNDS

Product	Durometer 10 Sec.	S.G.	Temp °C	Tensile	Elongation	LOI	Cold Impact	Application
OW125	70	1.25	105	2600	450	25	-20	SEOW JACKET
OW127	75	1.32	105	2000	350	30	-25	TPE WIND POWER JACKET
OW130XF	72	1.30	105	1900	370	27	-25	SEOW JACKET
OW138	67	1.29	105	1800	325	29	-40	TPE WIND POWER JACKET