



MATERIAL SELECTION GUIDE

TPO

FLEXIBLE CORD JACKET COMPOUNDS

Product	Durometer 10 Sec.	S.G.	Temp °C	Tensile	Elongation	LOI	Application
OTE6519	65	1.19	125	1500	650	17	JACKETING/INSULATION
OTO7510EP1	75	1.01	75	2000	450	17	TPO JACKET
OTO9097	90	0.95	75	2500	400	17	TPO JACKET
OTO9588	95	0.88	90	3600	500	17	TPO JACKET
OTR8588	85	0.88	125	2500	600	17	TPR JACKET