



MATERIAL SELECTION GUIDE

LOW SMOKE PVC

PLENUM INSULATION COMPOUNDS

Product	Durometer 10 Sec.	S.G.	Temp °C	Tensile	Elongation	LOI	Application
PL1001-1UV	58 "D"	1.60	75	2500	200	55	CMP, CL2P, FPLP, CAT3, CAT5/5E, CAT6
PL1001-3	60 "D"	1.62	75	2500	200	55	CMP, CL2P, FPLP, CAT3, CAT5/5E, CAT6
PL1001-8	60 "D"	1.62	75	2500	240	55	CMP, CL2P, FPLP, CAT3, CAT5/5E, CAT6
PL1001-11	60 "D"	1.60	75	2500	250	55	CAT5/5E