



## MATERIAL SELECTION GUIDE

### ZERO HALOGEN

#### RISER INSULATION COMPOUNDS

Product	Durometer 10 Sec.	S.G.	Temp °C	Tensile	Elongation	LOI	Application
OTO8150LSZH	80	1.50	90	1500	225	39	LOW SMOKE, ZERO HALOGEN
OTO9060LSZH	90	1.60	90	1500	150	45	LOW SMOKE, ZERO HALOGEN
OTO9141LSZH	91	1.41	90	1200	300	34	LOW SMOKE, ZERO HALOGEN
OTO9150LSZH	90	1.50	105	1500	225	37	LOW SMOKE, ZERO HALOGEN