



MATERIAL SELECTION GUIDE

ZERO HALOGEN

RISER JACKET COMPOUNDS

Product	Durometer 10 Sec.	S.G.	Temp °C	Tensile	Elongation	LOI	Application
OTO8150LSZH	80	1.50	90	1500	225	39	LOW SMOKE, ZERO HALOGEN
OTO8550	87	1.50	90	1500	200	35	LOW SMOKE, ZERO HALOGEN
OTO8580	85	1.60	90	1500	225	39	LOW SMOKE, ZERO HALOGEN
OT09060LSZH	90	1.60	90	1500	150	45	LOW SMOKE, ZERO HALOGEN
OTO9141LSZH	91	1.41	90	1200	300	34	LOW SMOKE, ZERO HALOGEN
OTO9150LSZH	90	1.50	105	1500	225	37	LOW SMOKE, ZERO HALOGEN
OTO9275	92	1.77	90	1200	200	45	LOW SMOKE, ZERO HALOGEN
XLO9141	91	1.41	90	1500	300	35	ZERO HALOGEN JACKET