



MATERIAL SELECTION GUIDE

PVC

TRAY CABLE INSULATION COMPOUNDS

Product	Durometer 10 Sec.	S.G.	Temp °C	Tensile	Elongation	LOI	Application
OW130	70	1.29	105	2000	350	30	MTW, 60°C OIL
OW132	92	1.32	105	3000	275	30	THHN, THWN, MTW, 60°C OIL
OW135	93	1.35	105	2600	220	29	THHN, THWN, THWN-2, MTW, 60°C OIL, SUNLIGHT 720 HR.