



MATERIAL SELECTION GUIDE

CPE

WIND POWER JACKET COMPOUNDS

Product	Durometer 10 Sec.	S.G.	Temp °C	Tensile	Elongation	Brittle Point	LOI	Application
OTE4535	45 "D"	1.35	105	1600	300	-35	33	CPE TRAY CABLE JACKET
OTE8541	85	1.40	105	2000	400	-35	36	TRAY CABLE JACKET
OTE8840-07	90	1.40	105	2000	250	-35	35	CPE/PVC BLEND TRAY CABLE JACKET