



THERMOPLASTIC COMPOUNDING

COMMITMENT TO INNOVATION &
TECHNOLOGY

FireFlex®T OTE5030

DESCRIPTION:

FireFlex®T OTE5030 IS A THERMOPLASTIC CHLORINATED POLYETHYLENE.

ASTM PROPERTIES

Specific Gravity	1.30	ASTM D792
Tensile Strength, psi	1400	ASTM D412
Elongation, %	300	ASTM D412
Polymer Type	TPO	---
Shore D Durometer	50	ASTM D2240

REVISION DATE 20-Feb-2023

This data is based on tests which are believed to be reliable. They are given as information only and since OTECH has no control over processing conditions or end use it cannot be responsible for the suitability of this product for any given application. Nothing stated above shall constitute a guarantee or warranty or shall be construed as a recommendation to use any product in conflicts with existing patents.

© 2023 OTECH CORPORATION All Rights Reserved.