



OTECH
FIREFLEX

THERMOPLASTIC COMPOUNDING

COMMITMENT TO INNOVATION &
TECHNOLOGY

OTE7030

DESCRIPTION:

Wire

ASTM PROPERTIES

Durometer,"A" 10 SEC.	67	ASTM D-2240
Specific Gravity	1.29	ASTM D792
Tensile Strength, psi	1800	ASTM D412
Elongation, %	325	ASTM D412
Limited Oxygen Index	29	ASTM D2863

This data is based on tests which are believed to be reliable. They are given as information only and since OTECH has no control over processing conditions or end use it cannot be responsible for the suitability of this product for any given application. Nothing stated above shall constitute a guarantee or warranty or shall be construed as a recommendation to use any product in conflicts with existing patents.

© 2023 OTECH CORPORATION All Rights Reserved.